



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08G 77/442, D21H 17/59	A1	(11) International Publication Number: WO 00/43440 (43) International Publication Date: 27 July 2000 (27.07.00)
(21) International Application Number: PCT/US00/01614 (22) International Filing Date: 25 January 2000 (25.01.00) (30) Priority Data: 60/117,166 25 January 1999 (25.01.99) US 09/449,261 24 November 1999 (24.11.99) US (71) Applicant: KIMBERLY-CLARK WORLDWIDE, INC. [US/US]; 401 N. Lake Street, Neenah, WI 54956 (US). (72) Inventors: SCHROEDER, Wen, Zyo; 3120 West Capitol Drive, Appleton, WI 54914 (US). CLARAHAN, Daniel, Arthur; 1642 Wayside Road, Greenleaf, WI 54126 (US). GOULET, Mike, Thomas; W7454 Ridgeside Drive, Neenah, WI 54956 (US). SHANNON, Thomas, Gerard; 1604 Meadowbreeze Circle, Neenah, WI 54956 (US). (74) Agents: CROFT, Gregory, E. et al.; Kimberly-Clark Worldwide, Inc., 401 N. Lake St., Neenah, WI 54956 (US).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: SYNTHETIC POLYMERS HAVING HYDROGEN BONDING CAPABILITY AND CONTAINING POLYSILOXANE MOIETIES (57) Abstract Synthetic polymers having hydrogen bonding capability and one or more polysiloxane moieties are capable of providing two distinct properties to paper products, such as tissues, which properties heretofore have been imparted through the use of at least two different molecules. The backbone of these synthetic polymers is based on modified vinyl polymers, such as polyvinyl alcohol, polyacrylamides and polyacrylic acids.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LI	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		

**Synthetic Polymers Having Hydrogen Bonding Capability and Containing
Polysiloxane Moieties**

Background of the Invention

In the manufacture of paper products, such as facial tissue, bath tissue, paper towels, dinner napkins and the like, a wide variety of product properties are imparted to the final product through the use of chemical additives. Examples of such additives include softeners, debonders, wet strength agents, dry strength agents, sizing agents, opacifiers and the like. In many instances, more than one chemical additive is added to the product at some point in the manufacturing process. Unfortunately, there are instances where certain chemical additives may not be compatible with each other or may be detrimental to the efficiency of the papermaking process, such as can be the case with the effect of wet end chemicals on the downstream efficiency of creping adhesives.

Another limitation, which is associated with wet end chemical addition, is the limited availability of adequate bonding sites on the papermaking fibers to which the chemicals can attach themselves. Under such circumstances, more than one chemical functionality competes for the limited available bonding sites, oftentimes resulting in the insufficient retention of one or both chemicals on the fibers. For more complex chemical systems it may desirable to have two or more functional additives retained in a specified ratio and/or spatial arrangement relative to one another. Although the addition of chemicals in a pre-determined ratio is easily achieved, retention of these chemicals in a predictable ratio is difficult using wet end chemical addition because of site competition and other influencing factors. Another limitation of either wet end or topical chemical addition is the inability to predictably locate functional chemical moieties in proximity to each other on the fiber surface.

Therefore, there is a need for a means of applying more than one chemical functionality to a paper web that mitigates the limitations created by limited number of bonding sites and the unpredictable nature of chemical additive retention which limits the ability to retain functional groups in a specified ratio and/or spatial arrangement with respect to one another.

Summary of the Invention

In certain instances, two or more chemical functionalities can be combined into a single molecule, such that the combined molecule imparts at least two distinct product properties to the final paper product that heretofore have been imparted through the use of two or more different molecules. More specifically, synthetic polymers, which are commonly used in the paper industry as dry strength resins, wet strength resins and retention aids, can be combined into a single molecule with polysiloxanes, which are utilized in the paper industry as surface modifiers, release agents, antifoams, softeners, debonders, lubricants and sizing agents. The resulting molecule is a synthetic polymer having hydrogen bonding capability and polysiloxane moieties which can provide several potential benefits, depending on the specific combination employed, including: strength aids that impart softness; softeners that do not reduce strength; wet strength with improved wet/dry strength ratio; surface feel modifiers with reduced linting and sloughing; strength aids with controlled absorbency; retention aids that soften; and improved retention of polysiloxanes when added as a wet end additive.

As used herein, "polysiloxanes" are macromolecules with a polymeric backbone of alternating silicon and oxygen atoms (i.e. siloxane bonds) of general structure $-(SiR_A R_B O)_n-$ where R_A and R_B are any organofunctional group and may be the same or different and n is an integer of 1 or greater. The "synthetic polymers", as described herein, have a portion of their structure derived from the polymerization of ethylenically unsaturated compounds which contain pendant groups that can form hydrogen bonds, ionic bonds or covalent bonds with cellulose molecules in fibers, thereby increasing interfiber bonding. They include polyacrylamide, polyvinyl alcohol, polyacrylic acid, polymaleic anhydride, polymaleic acid, polyitaconic acid, cationic polyacrylamides, anionic polyacrylamides, and the like. The synthetic polymers as described herein may be water soluble, organic soluble or soluble in mixtures of water and water miscible organic compounds. Preferably they are water-soluble or water dispersible but this is not a necessity of the invention. Also included within the definition are the salts of the above mentioned acidic polymers. Substances which can be combined with the acidic portion of the polymers to make the salts include the alkali metals such as K and Na usually added in form of their hydroxides, the aliphatic amines and alkanol amines, such salts and methods of preparing such salts being well known to those skilled in the art.

Depending upon the chemical and the desired impact on the paper sheet, the synthetic polymers of this invention may be applied to the paper web by any of the means known to those skilled in the art. Such means include wet end addition, spray addition on

the wet web, as a creping chemical sprayed on the Yankee dryer, or as a post treatment addition, including spraying, printing or coating.

Hence in one aspect, the invention resides in a synthetic polymer having hydrogen or covalent bonding capability and containing one or more polysiloxane moieties, said

5 synthetic polymer having the following structure (structure 1):



where:

a, b > 0;

c, d ≥ 0 such that c+d > 0;

10 w ≥ 1;

Q₁ = a monomer unit or a block or graft copolymer containing a pendant group capable of forming hydrogen or covalent bonds with cellulose. Preferred pendant groups for hydrogen bonding are —CONH₂, —COOH, —COO[−] M⁺, —OH and mixtures of said groups. Preferred pendant groups for covalent bonding are aldehydes and anhydrides. M⁺ can be any suitable counter ion including Na⁺, K⁺, Ca⁺² and the like.

15 Q₂ = a block or graft copolymer containing the siloxane bonds (—Si R_AR_BO—). The R_A and R_B functional groups attached to the Si atom can be alkyl or aliphatic hydrocarbons, linear or branched or cyclic, saturated or unsaturated, substituted or unsubstituted (e.g., containing —OH, —(EtO)_n, —(PO)_n, —COO—, —O—, —CONH—, —CONH₂—, —CO—, ...etc). Q₂ may take the form of —Z₁—Q₂—Z₁'— where Z₁, Z₁' are any bridging radicals, the same or different, whose purpose is to provide incorporation into the polymer backbone and Q₂ is as defined previously;

20 Q₃ = a monomer unit or a block or graft copolymer containing a charge functionality. Such charge functionality is preferably cationic but may be anionic or amphoteric; and


25 Q₄ = a monomer unit or a block or graft copolymer containing a hydrophilic moiety, which is desirable for making the material into a form suitable for papermaking. Q₄ may take the form of —Z₂—Q₄—Z₂'— where Z₂, Z₂' are any bridging radicals, the same or different, whose purpose is to provide incorporation into the polymer backbone and Q₄ is as defined previously. Q₄ may be incorporated to offset the increased polymer hydrophobicity caused by introduction of the polysiloxane moieties.

30 Examples of suitable Q₄ moieties are (but not limited to) the aliphatic polyether

derivatives of the formula $—[(CR_1R_2)_xO]_y—R_3$, wherein R_1 , R_2 is H or CH_3 , $x \geq 2$, $y \geq 1$ and R_3 is any suitable terminal group including $-CH_3$, $-H$, $-C_2H_5$, $-NH_2$.

It should be appreciated that when the Q_3 or other charged moiety is present in the synthetic polymer, that a suitable counterion will be necessary. Such counterions may or may not be represented in the formulas. Where such counterions are not represented in the formula it should be understood that such an ion will exist. The specific counterion is not critical for the invention, such counterion is only necessary for providing charge balance. For cationically charged groups the most common anions are those of the halides and alkyl sulfates. For anionically charged groups on the polymer the most common counter ions will be those of the alkali and alkaline earth metals as well as ammonia and amine derivatives.

More specifically, the invention resides in a synthetic polymer having the following
15 structure (structure 2):



where:

$$w \geq 1;$$
$$R_1, R_1', R_2, R_3 = H, C_{1-4} \text{ alkyl};$$

20 $a, b > 0$;

$c, d \geq 0$ such that $c+d > 0$;

Q_4 = a monomer unit or a block or graft copolymer containing a hydrophilic moiety, which is desirable for making the material into a form suitable for papermaking. Q_4 may take the form of $-Z_2-Q_4-Z_2'$ where Z_2 , Z_2' are any bridging radicals, the same or different, whose purpose is to provide incorporation into the polymer backbone and Q_4 is as defined previously. Q_4 may be incorporated to offset the increased polymer hydrophobicity caused by introduction of the polysiloxane moieties.

25 or different, whose purpose is to provide incorporation into the polymer backbone and Q₄ is as defined previously. Q₄ may be incorporated to offset the increased polymer hydrophobicity caused by introduction of the polysiloxane moieties. Examples of suitable Q₄ moieties are (but is not limited to) the aliphatic polyether derivatives of the formula —[(CR₁R₂)_xO]_y—R₃, wherein R₁, R₂ is H or CH₃, x ≥ 2, y
30 ≥ 1 and R₃ is any suitable terminal group including -CH₃, -H, -C₂H₅, -NH₂;

R_0 = any group capable of forming hydrogen or covalent bonds with cellulose.

Preferred are $-\text{CONH}_2$, $-\text{COOH}$, COO^-M^+ , $-\text{OH}$, $-\text{CONHCHOHCHO}$ and mixtures of said groups;

$A_1 = -H, -COOH;$

$R_4 = Z - R_6$ radical where:

$Z =$ aryl, $-CH_2-$, $-COO-$, $-CONR'-$, $-O-$, $-S-$, $-OSO_2O-$, $-CONHCO-$, $-CONHCHOHCHOO-$ or any other radical capable of bridging the R_6 group to the vinyl backbone portion of the molecule. ($R' = H$, alkyl);

$R_6 =$ a block or graft copolymer containing siloxane bonds;

$R_5 = Z_3 - R_{10} - W;$


$Z_3 =$ aryl, $-CH_2-$, $-COO-$, $-CONH-$, $-O-$, $-S-$, $-OSO_2O-$, any radical capable of bridging the R_{10} group to the vinyl backbone portion of the molecule;

$R_{10} =$ any linear or branched, aliphatic or aromatic hydrocarbon of 2 or more carbons, preferably $-(CH_2CH_2)-$, $-C(CH_3)_2CH_2CH_2-$; and


$W = -N^+R_{11}, R_{12}, R_{13}$ where R_{11}, R_{12}, R_{13} is a C_{1-4} alkyl group.

$-[CH_2CR_3R_5]_c-$ may also be the residue formed by co-polymerization with dimethyldiallyl ammonium chloride. In this case the charge-containing residue

$-[CH_2CR_3R_5]_c-$ will be the form of monomers with repeat units of structure:



In another aspect, the invention resides in a paper sheet, such as a tissue sheet, comprising a synthetic polymer having hydrogen bonding capability and containing an polysiloxane moiety, said polymer having the following structure:



where:

$a, b > 0;$

$c, d \geq 0;$

$w \geq 1;$


$Q_1 =$ a monomer unit or a block or graft copolymer containing a pendant group capable of forming hydrogen or covalent bonds with cellulose. Preferred pendant groups for hydrogen bonding are $-CONH_2$, $-COOH$, $-COO^- M^+$, $-OH$ and mixtures of said groups. Preferred pendant groups for covalent bonding are aldehydes and anhydrides. M^+ can be any suitable counter ion including Na^+ , K^+ , Ca^{+2} and the like;

$Q_2 =$ a block or graft copolymer containing the siloxane bonds $(-\text{Si } R_A R_B \text{O}-)$. The R_A and R_B functional groups attached to the Si atom can be alkyl or aliphatic hydrocarbons, linear or branched or cyclic, saturated or unsaturated, substituted or unsubstituted (e.g., containing $-\text{OH}$, $-(\text{EtO})_n$, $-(\text{PO})_n$, $-\text{COO}-$, $-\text{O}-$, $-\text{CONH}-$, $-\text{CONH}_2-$, $-\text{CO}-$, ...etc). Q_2 may take the form of $-\text{Z}_1-\text{Q}_2-\text{Z}_1'-$ where Z_1 , Z_1' are any bridging radicals, the same or different, whose purpose is to provide incorporation into the polymer backbone and Q_2 is as defined previously;

$Q_3 =$ a monomer unit or a block or graft copolymer containing a charge functionality. Such charge functionality is preferably cationic but may be anionic or amphoteric; and

$Q_4 =$ a monomer unit or a block or graft copolymer containing a hydrophilic moiety, which is desirable for making the material into a form suitable for papermaking. Q_4 may take the form of $-\text{Z}_2-\text{Q}_4-\text{Z}_2'-$ where Z_2 , Z_2' are any bridging radicals, the same or different, whose purpose is to provide incorporation into the polymer backbone and Q_4 is as defined previously. Q_4 may be incorporated to offset the increased polymer hydrophobicity caused by introduction of the polysiloxane moieties. Examples of suitable Q_4 moieties are (but is not limited to) the aliphatic polyether derivatives of the formula $-\text{[(CR}_1\text{R}_2)_x\text{O]}_y-\text{R}_3$, wherein R_1 , R_2 is H or CH_3 , $x \geq 2$, $y \geq 1$ and R_3 is any suitable terminal group including $-\text{CH}_3$, $-\text{H}$, $-\text{C}_2\text{H}_5$, $-\text{NH}_2$.

More specifically, the invention resides in a paper sheet, such as a tissue sheet, comprising a synthetic polymer having hydrogen bonding capability and containing an polysiloxane moiety, said polymer having the following structure:



where:

$w \geq 1$;

$\text{R}_1, \text{R}_1', \text{R}_2, \text{R}_3 = \text{H}, \text{C}_{1-4} \text{ alkyl};$

$a, b > 0$;

$c, d \geq 0$;

$Q_4 =$ a monomer unit or a block or graft copolymer containing a hydrophilic moiety, which is desirable for making the material into a form suitable for papermaking. Q_4 may take the form of $-\text{Z}_2-\text{Q}_4-\text{Z}_2'-$ where Z_2 , Z_2' are any bridging radicals, the same or different, whose purpose is to provide incorporation into the polymer backbone and Q_4 is as defined previously. Q_4 may be incorporated to offset the increased

polymer hydrophobicity caused by introduction of the polysiloxane moieties.

Examples of suitable Q_4 moieties are (but is not limited to) the aliphatic polyether derivatives of the formula $—[(CR_1R_2)_xO]_y—R_3$, wherein R_1, R_2 is H or CH_3 , $x \geq 2$, $y \geq 1$ and R_3 is any suitable terminal group including $-CH_3$, $-H$, $-C_2H_5$, $-NH_2$;

5 $R_0 =$ any group capable of forming hydrogen or covalent bonds with cellulose.

Preferred are $-CONH_2$, $-COOH$, COO^-M^+ , $-OH$, $-CONHCHOHCHO$, and anhydride including mixtures of said groups;

$A_1 =$ H, $COOH$;

$R_4 =$ Z - R_6 radical where:

10 $Z =$ aryl, $-CH_2-$, $-COO-$, $-CONR'-$, $-O-$, $-S-$, $-OSO_2O-$, $-CONHCO-$, $-CONHCHOHCHOO-$ or any radical capable of bridging the R_6 group to the vinyl backbone portion of the molecule. ($R' = -H$, alkyl);

$R_6 =$ a block or graft copolymer containing siloxane bonds;


$R_5 =$ $Z_3-R_{10}-W$;

15 $Z_3 =$ aryl, $-CH_2-$, $-COO-$, $-CONH-$, $-O-$, $-S-$, $-OSO_2O-$ or any radical capable of bridging the R_{10} group to the vinyl backbone portion of the molecule;


$R_{10} =$ any linear or branched, aliphatic or aromatic hydrocarbon of 2 or more carbons, preferably $-(CH_2CH_2)-$, $-C(CH_3)_2CH_2CH_2-$; and

$W = -N^+R_{11}, R_{12}, R_{13}$ where R_{11}, R_{12}, R_{13} is a C_{1-4} alkyl group.

20 $-[CH_2CR_3R_5]_c-$ may also be the residue formed by co-polymerization with dimethyldiallyl ammonium chloride. In this case the charge-containing residue $-[CH_2CR_3R_5]_c-$ will be the form of monomers with repeat units of structure:



25 In another aspect, the invention resides in a method of making a paper sheet, such as a tissue sheet, comprising the steps of: (a) forming an aqueous suspension of papermaking fibers; (b) depositing the aqueous suspension of papermaking fibers onto a forming fabric to form a web; and (c) dewatering and drying the web to form a paper sheet, wherein a synthetic polymeric additive is added to the aqueous suspension of
30 fibers or to the web, said polymeric additive having the following structure:



where:

a, b > 0;

c, d ≥ 0;

5 w ≥ 1;

Q₁ = a monomer unit or a block or graft copolymer containing a pendant group capable of forming hydrogen or covalent bonds with cellulose. Preferred pendant groups for hydrogen bonding are —CONH₂, —COOH, —COO[−] M⁺, —OH and mixtures of said groups. Preferred pendant groups for covalent bonding are aldehydes and anhydrides. M⁺ can be any suitable counter ion including Na⁺, K⁺, Ca⁺² and the like;


10 Q₂ = a block or graft copolymer containing the siloxane bonds (—Si R_AR_BO—). The R_A and R_B functional groups attached to the Si atom can be alkyl or aliphatic hydrocarbons, linear or branched or cyclic, saturated or unsaturated, substituted or unsubstituted (e.g., containing —OH, —(EtO)_n, —(PO)_n, —COO—, —O—, —CONH—, —CONH₂—, —CO—, ...etc). Q₂ may take the form of —Z₁—Q₂—Z₁'— where Z₁, Z₁' are any bridging radicals, the same or different, whose purpose is to provide incorporation into the polymer backbone and Q₂ is as defined previously;

15 Q₃ = a monomer unit or a block or graft copolymer containing a charge functionality. Such charge functionality is preferably cationic but may be anionic or amphoteric; and

20 Q₄ = a monomer unit or a block or graft copolymer containing a hydrophilic moiety, which is desirable for making the material into a form suitable for papermaking. Q₄ may take the form of —Z₂—Q₄—Z₂'— where Z₂, Z₂' are any bridging radicals, the same or different, whose purpose is to provide incorporation into the polymer backbone and Q₄ is as defined previously. Q₄ may be incorporated to offset the increased polymer hydrophobicity caused by introduction of the polysiloxane moieties. Examples of suitable Q₄ moieties are (but is not limited to) the aliphatic polyether derivatives of the formula —[(CR₁R₂)_xO]_y—R₃, wherein R₁, R₂ is —H or —CH₃, x ≥ 2, y ≥ 1 and R₃ is any suitable terminal group including —CH₃, —H, —C₂H₅, —NH₂.

25 More specifically, the invention resides in a method of making a paper sheet, such as a tissue sheet, comprising the steps of: (a) forming an aqueous suspension of papermaking fibers; (b) depositing the aqueous suspension of papermaking fibers onto a

forming fabric to form a web; and (c) dewatering and drying the web to form a paper sheet, wherein a synthetic polymeric additive is added to the aqueous suspension of fibers or to the web, said polymeric additive having the following structure:




- 5 where:
- $w \geq 1$;
- $R_1, R_1', R_2, R_3 = \text{H, C}_{1-4} \text{ alkyl}$;
- $a, b > 0$;
- $c, d \geq 0$;
- 10 $Q_4 =$ a monomer unit or a block or graft copolymer containing a hydrophilic moiety, which is desirable for making the material into a form suitable for papermaking. Q_4 may take the form of $-Z_2-Q_4-Z_2'$ where Z_2, Z_2' are any bridging radicals, the same or different, whose purpose is to provide incorporation into the polymer backbone and Q_4 is as defined previously. Q_4 may be incorporated to offset the increased
- 15 polymer hydrophobicity caused by introduction of the polysiloxane moieties. Examples of suitable Q_4 moieties are (but is not limited to) the aliphatic polyether derivatives of the formula $-\text{[(CR}_1\text{R}_2)_x\text{O}]_y-\text{R}_3$, wherein R_1, R_2 is H or CH_3 , $x \geq 2$, $y \geq 1$ and R_3 is any suitable terminal group including $-\text{CH}_3, -\text{H}, -\text{C}_2\text{H}_5, -\text{NH}_2$;
- $R_0 =$ any group capable of forming hydrogen or covalent bonds with cellulose.
- 20 Preferred are $-\text{CONH}_2, \text{COOH}, \text{COO}^-, -\text{OH}, \text{CONHCHOHCHO}$, and anhydride including mixtures of said groups;
- $A_1 = -\text{H}, -\text{COOH}$;
- $R_4 = Z - R_6 - Y$ radical where:
- $Z =$ aryl, $-\text{CH}_2-, -\text{COO-}, -\text{CONR}'-, -\text{O-}, -\text{S-}, -\text{OSO}_2\text{O-}, -\text{CONHCO-}, -$
- 25 CONHCHOHCHOO- or any radical capable of bridging the R_6 group to the vinyl backbone portion of the molecule. ($R' = \text{H, alkyl}$);
- $R_6 =$ a block or graft copolymer containing siloxane bonds;
- $Y = \text{H}, -\text{N}^+\text{R}_{11}, \text{R}_{12}, \text{R}_{13}, -\text{NR}_7\text{R}_8$, where R_7, R_8, R_9 are same or different and are H or C_{1-30} linear or branched, saturated or unsaturated aliphatic hydrocarbons;
- 30 At least one of R_6, R_7, R_8, R_9 must be an aliphatic, linear or branched, substituted or non-substituted, hydrocarbon of chain length 8 or higher;
- $R_5 = Z_3 - R_{10} - W$;

$Z_3 =$ aryl, $-\text{CH}_2-$, $-\text{COO}-$, $-\text{CONH}-$, $-\text{O}-$, $-\text{S}-$, $-\text{OSO}_2\text{O}-$ or any radical capable of bridging the R_{10} group to the vinyl backbone portion of the molecule;

$\text{R}_{10} =$ any linear or branched, aliphatic or aromatic hydrocarbon of 2 or more carbons, preferably $-(\text{CH}_2\text{CH}_2)-$, $-\text{C}(\text{CH}_3)_2\text{CH}_2\text{CH}_2-$; and

5 $\text{W} = -\text{N}^+ \text{R}_{11}, \text{R}_{12}, \text{R}_{13}$ where $\text{R}_{11}, \text{R}_{12}, \text{R}_{13}$ is a C_{1-4} alkyl group.

$-\text{[CH}_2\text{CR}_3\text{R}_5\text{]}_c-$ may also be the residue formed by co-polymerization with dimethyldiallyl ammonium chloride. In this case the charge-containing residue $-\text{[CH}_2\text{CR}_3\text{R}_5\text{]}_c-$ will be the form of monomers with repeat units of structure:



10

The amount of the synthetic polymeric additive added to the fibers or the tissue web can be from about 0.02 to about 4 weight percent, on a dry fiber basis, more specifically from about 0.05 to about 2 weight percent, and still more specifically from about 0.1 to about 1 weight percent. The synthetic polymer can be added to the fibers or web at any point in the process, but it can be particularly advantageous to add the synthetic polymer to the fibers while the fibers are suspended in water.

15

Methods of making paper products which can benefit from the various aspects of this invention are well known to those skilled in the papermaking art. Exemplary patents include U.S. Patent No. 5,785,813 issued July 28, 1998 to Smith et al. entitled "Method of Treating a Papermaking Furnish For Making Soft Tissue"; U.S. Patent No. 5,772,845 issued June 30, 1998 to Farrington, Jr. et al. entitled "Soft Tissue"; U.S. Patent No. 5,746,887 issued May 5, 1998 to Wendt et al. entitled "Method of Making Soft Tissue Products"; and U.S. Patent No. 5,591,306 issued January 7, 1997 to Kaun entitled "Method For Making Soft Tissue Using Cationic Silicones", all of which are hereby incorporated by reference.

20

25

Detailed Description of the Invention

30

To further describe the invention, examples of the synthesis of some of the various chemical species are given below.


Modified Vinyl Polymers

First with regard to the modified vinyl polymers, they can be made via free radical polymerization of vinyl monomers of the form:



- 5 where R_1, R_2, R_3, R_4 may be H, halogen, alkyl, functional alkyl, aryl, functional aryl. For papermaking the polyacrylamides ($R_4 = \text{---CONH}_2$), polyvinyl alcohols ($R_4 = \text{---OH}$), and polyacrylates ($R_4 = \text{---COOR}'$, $R' = \text{H, Me}$) are the most widely used.

Of the modified vinyl polymers, polyacrylamides (PAMs) are used as dry strength additives in addition to their widespread use as drainage and retention aids. They are
 10 water-soluble polymers containing primary amide groups that can form hydrogen bonds with cellulose molecules in fibers thereby increasing interfiber bonding. They are synthesized by the free radical polymerization of acrylamide as shown in Reaction 1.



15


Reaction 1

PAMs are nonionic materials and have very little attraction to papermaking fibers. Therefore it is necessary to incorporate charged groups into the polymer structure to make it useful for papermaking. Both anionic and cationic polyacrylamides are known in
 20 the art.

Anionic polyacrylamides can be produced by : (1) copolymerization of acrylamide with acrylic acid; and (2) hydrolysis of some of the amide groups on the polyacrylamide chain. The resultant polymer will contain a mixture of acrylamide and acrylic acid groups. Anionic polyacrylamides were first produced in the 1950's via copolymerization of
 25 acrylamide with acrylic acid. The acrylic acid groups introduce an ionizable carboxyl group on the polymer backbone. Ionization of these carboxyl groups is highly pH dependent where above pH 7 essentially 100% of the carboxyl groups are ionized. Since anionic polyacrylamides are negatively charged they are not directly attracted to the like charged cellulose fibers. A cationic substance such as alum must be used in conjunction
 30 with them to promote their retention.


To avoid the need for a cationic promoter, another approach is to incorporate cationic groups directly into the polymer backbone. Having been commercially produced since the late 1960's these cationically charged polyacrylamides are the most common form of dry strength PAM's. Cationic polyacrylamides are produced by copolymerization

of acrylamide with cationic monomers or by modification of some of the amide groups. A typical reaction is illustrated in Reaction 2 for co-polymerization with Methacryloyloxyethyl trimethyl ammonium methosulfate (METAMS). Typical cationic monomers include: (1) methacryloyloxyethyl trimethyl ammonium methosulfate; (2) dimethyldiallyl ammonium chloride (DMAAC); (3) 3-acryloamido-3-methyl butyl trimethyl ammonium chloride (AMBTAC); (4) trimethylamino methacrylate; and (5) vinyl benzyl trimethyl ammonium chloride (VBTAC). Such materials have structures similar to that shown in Reaction 2 for METAMS copolymerized cationic PAM.



Reaction 2

The incorporation of cationic groups through modification of non-ionic polyacrylamide is most often accomplished via the Mannich reaction as illustrated in Reaction 3. Generally cationic polyacrylamides will contain from about 5 to about 70% mole percent cationic groups.



Reaction 3

Generally dry strength PAMs are supplied as ready to use aqueous solutions or as water-soluble powders which must be dissolved prior to use. They may be added to thin or thick stock at a point of good mixing for best results. Addition rates of 0.1% to 0.5% of

dry fiber typically give best results. High addition rates may cause overcationization of the furnish and reduce the effectiveness of other additives.

When used as dry strength additives usually around 10 mole % of the monomers will contain charged groups. Unlike the anionic PAM's, cationic PAM's are effectively charged across the entire pH range. Typical molecular weights for cationic PAM dry strength aids are in the range of 100,000 to 500,000. The molecular weight is important so as to be low enough to not bridge between particles and cause flocculation, and yet high enough to retard migration of the polymer into the pores of the fibers. Such migration would cause a reduction in dry strength activity.

When used as retention aids a broader range of molecular weights and charge densities may be employed. Key characteristics of polyacrylamide retention aids include the molecular weight, the type of charge, the charge density and the delivery form. For the average molecular weight, the range can be: low (1,000 - 100,000); medium (100,000 - 1,000,000); high (1,000,000 - 5,000,000); very high (>5,000,000). The charge type can be nonionic, cationic, anionic or amphoteric. The charge density can be: low (1 - 10%); medium (10 - 40%); high (40 - 80%); or very high (80 - 100%). The delivery form can be either an emulsion, an aqueous solution or a dry solid.

High molecular weight/low charge density flocculants are used most often for retention of fine particles in high shear and turbulence environments. Low molecular weight/high charge density products are used for their charge modifying capabilities and for retention in low shear environments.

Polysiloxanes

With regard to the polysiloxane component, polysiloxanes can be made using a three-step synthesis: chlorosilane synthesis, chlorosilane hydrolysis, followed by polymerization and polycondensation.

Chlorosilane Synthesis:




where:

R = H, methyl or ethyl group, and


R'₄ = Cl, H, methyl or ethyl.

This reaction is exothermic with a yield as high as 90%. A copper-based catalyst is usually used. The resulting various chloroalkylsilanes can be separated by fractionation


distillation. If desired, silanes of other functionalities can be obtained via further reactions. For instance:



5



10



where


R = alkyl, aryl, or other organofunctional group.

R' = methyl, ethyl or acetoxy

15

Chlorosilane Hydrolysis:

Dimethyldichlorosilanes undergo exothermic hydrolysis to yield disilanol which further condense to produce a variety of linear and/or cyclic oligomers:



n = 20-50; and

m ≥ 3

25

The linear and cyclic oligomers from the above hydrolysis need to be further polymerized or condensed to produce a silicone macromolecule of sufficient length.

Cyclic Polymerization

30

The (R₂SiO)_n cyclic oligomers undergo ring opening and polymerization to form long linear chains. Polymer chain length are determined by the presence (concentration) of the chain endblocker.




wherein

$$m \geq 1$$

$$n \geq 3$$

$$5 \quad z \geq 1$$

Copolymerization in the presence of a catalyst (Me_4NOH) can be carried out in the following scheme:



10 where


R = alkyl, aryl, or other organofunctional group.

$$X \geq 1$$

$$n \geq 4$$

15 Linear Condensation

The linear silanol condenses to give long chain siloxanes.



where

R = alkyl, aryl, or other organofunctional group

20


Attached to the silicon atom are organic side chains including alkyl, aliphatic hydrocarbons, phenyl or vinyl groups. By adjusting the --SiO-- chain length, the side chain functionality and the crosslinking between molecular chains, silicones form an almost infinite number of hybrid polymers. In fact, the industry has created a plethora of novel silicones to provide various end use properties such as chemical compatibility, solubility, water repellency, lubrication, foam control, releasing aid, cooling, sealing, adhesion, coating and substantivity.

25

Organoreactive polysiloxanes and silanes are very useful in making hybrid polymers. The following are a few examples:

30

Copolymerization of vinyl silanes with an organic monomer:



where

R_3 and R' are chlorine, amine, methoxy, acetoxy, hydroxyl, vinyl, or silicone hydride functionalities

5 $x \geq 1$

$y \geq 1$

Grafting the silicones to an organic polymer backbone:




10 where

R and R' are chlorine, amine, methoxy, acetoxy, hydroxyl, vinyl, or silicone hydride functionalities

$x \geq 1$

15 Addition of silicone functionality:



where

R' = any organofunctional group

R = alkyl, aryl, or other organofunctional group.

20

Modified Vinyl Polymers Containing Polysiloxanes

There are several envisioned pathways in which synthetic polymers containing hydrogen bonding groups and polysiloxanes can be combined onto a single molecule (structures 1 and 2) for purposes of this invention. These include, but are not limited to:

25 (1) block co-polymerization and/or grafting ; (2) direct monomer incorporation ; and (3) derivatization of functional groups on the polymer backbone. Each of these methods is described below.-Since these materials maintain their bonding and/or charge characteristics they would be expected to maintain their dry strength and or retention capabilities as well as provide for materials with enhanced tactile properties due to
30 introduction of the polysiloxane moieties.

The molar and weight ratios of the various functional groups on the polymer will largely depend on the specific application of the material and is not a critical aspect of the

invention. However, with regard to structure 1, the portion of the synthetic polymer [Q₁] capable of forming hydrogen, covalent and ionic bonds can constitute from about 10 to about 90 weight percent of the total polymer, more specifically from about 20 to about 80 weight percent of the total polymer and still more specifically from about 30 to about 70 weight percent of the total polymer. The polysiloxane portion [Q₂] of the synthetic polymer can constitute from about 10 to about 90 weight percent of the synthetic polymer, more specifically from about 20 to about 80 weight percent of the synthetic polymer and still more specifically from about 30 to about 70 weight percent of the synthetic polymer. The charge containing portion [Q₃] of the synthetic polymer can be comprised of monomer units constituting from 0 to about 80 mole percent of the total monomer units in the synthetic polymer, more specifically from 0 to about 30 mole percent and still more specifically from about 5 to about 15 mole percent. The [Q₄] functionality will be comprised of monomer units constituting from 0 to about 80 mole percent of the total monomer units in the synthetic polymer, more specifically from 0 to about 40 mole percent and still more specifically from 0 to about 20 mole percent.

Likewise the molecular weight of the synthetic polymers of the present invention will largely depend on the specific application of the material and is not overly critical to the invention. The weight average molecular weight range can be from about 1,000 to about 5,000,000, more specifically from about 10,000 to about 2,000,000 and still more specifically from about 20,000 to about 1,000,000. Where these polymers are added for dry strength it is important that the molecular weight of the polymer be low enough so as to not bridge between particles and cause flocculation, and yet high enough so as to retard migration of the polymer into the pores of the fibers. These materials can have weight average molecular weights in the range of from about 5,000 to about 1,000,000, more specifically from about 10,000 to about 1,000,000 and still more specifically from about 20,000 to about 600,000.


Block copolymerization and/or grafting.

In this aspect of the invention one or more of the [Q]_i elements of the polymer exists as a block or graft copolymer on the vinyl backbone. These synthetic polymers are distinguished from those of the direct monomer incorporation in that the polysiloxane portion of the molecule would be incorporated linearly within the polymer chain rather than in a pendant fashion. It should be appreciated that any of the synthetic polymer elements or combination of the synthetic polymer elements Q₁, Q₂, Q₃, Q₄ could be incorporated via this approach. Note that where a polyacrylamide is employed that these polymers

maintain pendant amide functionality and are therefore capable of being glyoxylated to form materials possessing temporary wet strength.

Direct monomer incorporation.

- 5 Incorporation of the polysiloxane moieties can be accomplished via copolymerization with vinyl type monomers containing aliphatic groups. Almost any vinyl type monomer containing a pendant polysiloxane moiety can be co-polymerized with acrylamide or a similar vinyl monomer containing a pendant hydrogen-bonding moiety to be incorporated into the polymer backbone. Generically the synthesis can be described
- 10 in Reaction 4.



Reaction 4

where:

- 15 $R_1, R_1', R_1'', R_1''', R_1'''' = H, C_{1-4} \text{ alkyl};$
 $a, b \geq 1;$
 $c, d \geq 0;$
 $w \geq 1;$
 $r, s \geq 1;$

20 $t, u \geq 0;$
 $a \cdot w = r;$
 $b \cdot w = s;$
 $c \cdot w = t;$
 $d \cdot w = u;$

R_0 = any group capable of forming hydrogen or covalent bonds with cellulose.

Preferred are $-\text{CONH}_2$, COOH , COO^- , $-\text{OH}$, CONHCHOHCHO , and anhydride including mixtures of said groups;

A_1 = H , COOH ;

5 R_4 = $Z - R_6 - Y$ radical where:

Z = Aryl, CH_2 , COO^- , $\text{CONH}-$, $-\text{O}-$, $-\text{S}-$, $-\text{OSO}_2\text{O}-$, $-\text{CONHCO}-$, $\text{CONHCHOHCHOO}-$, any radical capable of bridging the R_6 group to the vinyl backbone portion of the molecule;

10 Y = H , $-\text{N}^+\text{R}_7\text{R}_8\text{R}_9$, $-\text{NR}_7\text{R}_8$, where R_7 , R_8 , R_9 are same or different and are H or C_{1-30} aliphatic hydrocarbons;

R_5 = any aliphatic, linear or branched, saturated or unsaturated, substituted or non-substituted hydrocarbon;

15 R_{14} = a moiety necessary for making the material into a form suitable for papermaking. R_{14} may take the form of $-\text{Z}_1-\text{R}_{14}$ where Z_1 is any bridging radical whose purpose is to provide incorporation into the polymer backbone and R_{14} is as defined previously. R_{14} may be incorporated to offset the increased polymer hydrophobicity caused by introduction of the polysiloxane moieties. Examples of suitable R_{14} moieties are (but is not limited to) the aliphatic polyether derivatives of the formula $-(\text{CR}_1\text{R}_2)_x\text{O}]_y-\text{R}_{15}$, wherein R_1 , R_2 is H or CH_3 , $x \geq 2$, $y \geq 1$ and R_{15} is
20 any suitable terminal group including $-\text{CH}_3$, $-\text{H}$, $-\text{C}_2\text{H}_5$, $-\text{NH}_2$, and the like; and

At least one of R_6 , R_7 , R_8 , R_9 must be a C_8 or higher linear or branched, saturated or unsaturated, substituted or non-substituted, aliphatic hydrocarbon.


More specifically, $R_5 = \text{Z}_3-\text{R}_{10}-\text{W}$, where:

25 Z_3 = Aryl, CH_2 , COO^- , $\text{CONH}-$, $-\text{O}-$, $-\text{S}-$, $-\text{OSO}_2\text{O}-$, any radical capable of bridging the R_{10} group to the vinyl backbone portion of the molecule;


R_{10} = any linear or branched, aliphatic or aromatic hydrocarbon of 2 or more carbons, preferably $-(\text{CH}_2\text{CH}_2)-$, $-\text{C}(\text{CH}_3)_2\text{CH}_2\text{CH}_2-$; and

$\text{W} = -\text{N}^+\text{R}_{11}\text{R}_{12}\text{R}_{13}$ where R_{11} , R_{12} , R_{13} is a C_{1-4} alkyl group.

30 R_5 can also be the residue formed by co-polymerization with dimethyldiallyl ammonium chloride. In this case the residue will be the form of monomers with repeat units of structure:



Polymers of the type shown in Reaction 4, which maintain pendant amide functionality, may further be modified to produce materials exhibiting temporary wet strength as well as dry strength. Most notably this may be accomplished through reaction
5 with glyoxal. The general reaction scheme is given in Reaction 5.




Reaction 5

10

Incorporation of polysiloxanes can be accomplished via two primary routes: a) incorporation via copolymerization with vinyl type monomers containing polysiloxanes or silane groups and b) reaction with functional groups attached to the modified polyvinyl backbone.

15

Almost any vinyl type polymer can be co-polymerized with acrylamide to be incorporated into the polymer backbone. Generically the synthesis can be described in Reaction 6.



$R_1, R_1', R_2, R_3 = H \text{ or } C_{1-4} \text{ alkyl or hydroalkyl}$

$a, b \geq 1$

$c \geq 0$

Reaction 6

5 where

$R_0 =$ any group capable of forming hydrogen bonds. Preferred but not limited to are -
CONH₂, OH, COOH, COO- including mixtures of said groups.

$A_1 =$ COOH, H

10 $Z =$ Ar, CH₂, COO-, CONH-, -O-, -S-, -OSO₂O-, -CONHCO-, -CONHCHOHCHOO-, or
any radical capable of bridging the R₆ group to the vinyl backbone portion of the
molecule.


15 $R_4 =$ Si(R')₂-O-[Si(R'')₂-O]_n-Si(R''')₃ where R', R'', R''' can be the same or different, are
selected from the following groups: H, OH, aryl, or alkyl or aliphatic hydrocarbon,
C₁₋₄₀, linear or branched, saturated or unsaturated, substituted or non-substituted,
with or without ethoxylation and/or propoxylation.

$R_5 =$ Z₃-R₁₀-W

$Z_3 =$ Ar, CH₂, COO-, CONH-, -O-, -S-, -OSO₂O-, any radical capable of bridging the
R₁₀ group to the vinyl backbone portion of the molecule.

20 $R_{10} =$ any linear or branched, aliphatic or aromatic hydrocarbon of 2 or more carbons,
preferably -(CH₂CH₂)-, -C(CH₃)₂CH₂CH₂-W = -N⁺R₁₁,R₁₂,R₁₃ where R₁₁, R₁₂, R₁₃ is
a C₁₋₄ alkyl group.

CH₂=CR₃R₅ may also be dimethyldiallyl ammonium chloride. In this case the residue will
be the form of monomers with repeat units of structure




25

A specific example is given as follows with synthesis shown in Reaction 7. Vinyl
siloxanes and polysiloxanes are known commercially available materials. They will have
the general structure R₁R₂ = R₃R₄ where R₄ will contain the siloxane or polysiloxane
moiety and R₁, R₂, R₃ can be H, or various organic radicals including alkyl, alkoxy, etc.

30 They would be expected to incorporate into any vinyl type polymer such as a PAM, PVA,

etc. They would be incorporated directly into the polymer during the polymerization process as described below. Description shown is specific for a polyacrylamide but is applicable to any vinyl type polymer. As such the siloxanes are arranged on the polymer in a pendant fashion.

5



Reaction 7

10 where

$\text{R}_1, \text{R}_2 = \text{H}, \text{OH}, \text{alkyl}, \text{hydroxyalkyl}, \text{substituted or unsubstituted}, \text{linear or branched of chain length } \text{C}_1\text{-}\text{C}_{30}, \text{ or } -(\text{CH}_2)_p - \text{O} - (\text{EtO})_q - (\text{PO})_r - \text{R}'_1, \text{ where } p \geq 0, q+r \geq 1$

$\text{R}'_1 = \text{H}, \text{Alkyl or hydroxyalkyl of } \text{C}_1 - \text{C}_{30}, \text{ substituted or unsubstituted}, \text{linear or branched};$


15 $\text{R} = \text{H}, \text{OH}, \text{alkyl}, \text{hydroxyalkyl}, \text{C}_1 - \text{C}_{30}, \text{ or } -(\text{CH}_2)_n - \text{N}(\text{R}')_2$

where

$\text{R}' = \text{H}, \text{alkyl}, \text{or hydroxyalkyl}, \text{substituted or unsubstituted}, \text{linear or branched}, \text{C}_1 - \text{C}_{30}$

20

Note that since these polymers maintain pendant amide functionality they are capable of being glyoxylated to form materials possessing temporary wet strength as shown in Reaction 8.



Reaction 8

5 where

$R_1, R_2 = \text{H, OH, alkyl, hydroxyalkyl, substituted or unsubstituted, linear or branched of chain length } C_1 - C_{30}, \text{ or } -(CH_2)_p - O - (EtO)_q - (PO)_r - R_1', \text{ where } p \geq 0, q+r \geq 1$

$R_1' = \text{H, Alkyl or hydroxyalkyl of } C_1 - C_{30}, \text{ substituted or unsubstituted, linear or branched;}$

10 $R = \text{H, OH, alkyl, hydroxyalkyl, } C_1 - C_{30}, \text{ or } --(CH_2)_n - N(R')_2$


where

$R' = \text{H, alkyl, or hydroxyalkyl, substituted or unsubstituted, linear or branched, } C_1 - C_{30}$

15 Derivatization of functional groups on the polymer backbone

The second approach to synthesis of materials of structures 1 and 2 is to modify the functional groups on the polymer backbone. The vinyl type polymers, including the modified polyacrylamides, polyacrylic acid and polyvinyl alcohol contain functional groups which may be further derivatized to produce materials of Reaction 4. The polymer

functional groups which may be reacted upon include but are not limited to: amide, acyl, carboxyl, hydroxyl, cyano, and aldehyde (from glyoxylation or similar reaction). In general the starting polymer will be one of that shown in the following structure 3:



5

Structure 3

where

$R_1, R_1', R_2, R_3 = \text{H, C}_{1-4} \text{ alkyl or hydroxyalkyl}$

$a, b \geq 1$

10 $c \geq 0$

$R_0 =$ any group capable of forming hydrogen bonds. Preferred are $-\text{CONH}_2$, COOH , OH , COO^- including mixtures of said groups.


15 $Z_4 =$ $-\text{CONHCHOHCHO}$, $-\text{CONH}_2$, $-\text{COOH}$, $-\text{R-CN}$, $-\text{OH}$, $-\text{SH}$, $-\text{NH}_2$, $-\text{OH}$ or any other functional group capable of being reacted upon in a manner so as to incorporate a polysiloxane chain, (substituted or unsubstituted) into the polymer.

$R_5 = Z_3-R_{10}-W$

$Z_2 =$ Ar , CH_2 , COO^- , $\text{CONH}-$, $-\text{O}-$, $-\text{S}-$, $-\text{OSO}_2\text{O}-$, any radical capable of bridging the R_{10} group to the vinyl backbone portion of the molecule.


20 $R_{10} =$ any linear or branched, aliphatic or aromatic hydrocarbon of 2 or more carbons, preferably $-(\text{CH}_2\text{CH}_2)-$, $-\text{C}(\text{CH}_3)_2\text{CH}_2\text{CH}_2-W = -\text{N}^+R_{11}, R_{12}, R_{13}$ where R_{11}, R_{12}, R_{13} is a C_{1-4} alkyl group.

$-\text{[CH}_2\text{CR}_3\text{R}_5\text{]}_c-$ may also be the residue formed by co-polymerization with dimethyldiallyl ammonium chloride. In this case the residue will be the form of monomers with repeat units of structure




25

Materials such as those shown in structure 3 are amenable to reaction with a large variety of reagents as a means of incorporating polysiloxanes into the polymer. A general derivatization scheme is shown in Reaction 9 with specific example given in Reaction 10.

**Reaction 9**

where

- 5 X = a functional end group including -Cl, -H, -OH attached to the polysiloxane capable of being reacted upon by a functional group attached to the other polymer in a manner so as to incorporate the polysiloxane moiety (substituted or unsubstituted, may contain various degrees of ethoxylation or propoxylation, may contain various functional linkages such as ester, ether, amide, or amine) into the polymer;
- 10 Y = the polysiloxane moiety.

**Reaction 10**

where

$x, y = 1 - 5000;$

$R, R', R'' = CH_3;$

$R'' = -(CH_2)_a - O - (C_2H_5O)_m - (C_3H_7O)_n - OH$


5 where

$a = 2-6;$

$m = 1-1000;$

$n = 1-500.$

10 If the end block functional groups are not reactive enough, silane coupling agents may be used to bridge the vinyl and the siloxane polymers. An example is shown in Reaction 11. Silane coupling agents have been used extensively by those skilled in the art to semipermanently modify a substrate. In the skin care area, they have been used with materials to provide long lasting protective benefits such as: (1) nonocclusive water
15 barriers to prevent over hydration of the skin; (2) humectants; (3) skin conditioners; (4) antimicrobials; and (5) sunscreens agents, etc. The same coupling agents can be bonded to a cellulosic substrate to attach, e.g., germicidal or lubricating function to a tissue or towel or wipe.



20

Reaction 11

where

x, y = 1 - 5000;

R, R', R'' = CH₃;

5 R'' = -(CH₂)_a - O - (C₂H₅O)_m - (C₃H₇O)_n - OH

where:

a = 2-6;

m = 1-1000;

n = 1-500.


10

It will be appreciated that the foregoing examples, given for purposes of illustration, are not to be construed as limiting the scope of this invention, which is defined by the following claims and all equivalents thereto.

15

We claim:

1. A synthetic polymer containing one or more polysiloxane moieties, said synthetic polymer having the following structure:



$a, b > 0$;

$c, d \geq 0$ such that $c+d > 0$;

$w \geq 1$;

- 10 $\text{Q}_1 =$ a monomer unit or a block or graft copolymer containing a pendant group capable of forming hydrogen or covalent bonds with cellulose;
- $\text{Q}_2 =$ a block or graft copolymer containing siloxane bonds ;
- $\text{Q}_3 =$ a monomer unit or a block or graft copolymer containing a charge functionality;
- and
- 15 $\text{Q}_4 =$ a monomer unit or a block or graft copolymer containing a hydrophilic moiety, which is desirable for making the material into a form suitable for papermaking.

2. The polymer of claim 1 wherein the pendant group on Q_1 capable of forming hydrogen or covalent bonds is selected from the group consisting of $-\text{CONH}_2$, $-\text{COOH}$, $-\text{COO}^-\text{M}^+$, $-\text{OH}$, $-\text{CONHCHOHCHO}$ or anhydrides and mixtures thereof, wherein M^+ is a counter ion.

3. The polymer of claim 1 wherein Q_2 is of the form $-\text{Z}_1-\text{Q}_2-\text{Z}_1'$ where Z_1, Z_1' are bridging radicals, which can be the same or different.

4. The polymer of claim 1 wherein Q_4 is of the form $-\text{Z}_2-\text{Q}_4-\text{Z}_2'$ where Z_2, Z_2' are bridging radicals, which can be the same or different.

5. The polymer of claim 1 wherein Q_4 is a radical of the form $-\text{CHR}_1\text{CR}_0\text{R}_1'-$ wherein R_0 is an aliphatic polyether derivative of the formula $-\text{[(CR}_2\text{R}_2')_x\text{O}]_y-\text{R}_3$ where:


R_1, R_1' is $-\text{H}$, C_{1-4} alkyl;

- 5 R_2, R_2' is $-\text{H}$ or $-\text{CH}_3$;

$x \geq 2$;


$y \geq 2$; and

R_3 is a terminal group selected from the group consisting of $-\text{CH}_3$, $-\text{H}$, $-\text{C}_2\text{H}_5$, and $-\text{NH}_2$.



6. The polymer of claim 1 wherein Q_3 is
7. The polymer of claim 1 wherein Q_3 is a radical of the form $\text{---CHR}_1\text{CR}_0\text{R}_1'\text{---}$ wherein
 R_0 = a pendant group of the form $Z_3\text{---R}_{10}\text{---W}$, where Z_3 is a radical bonding the R_{10} group to the polymer;
 R_1 and R_1' are $-\text{H}$ or a C_{1-4} alkyl group;
 R_{10} = any linear or branched, aliphatic or aromatic hydrocarbon of 2 or more carbons; and
 $W = -\text{N}^+\text{R}_{11}\text{R}_{12}\text{R}_{13}$ where R_{11} , R_{12} , R_{13} is a C_{1-4} alkyl group.
8. The polymer of claim 7 wherein Z_1 is selected from the group consisting of aryl, $-\text{CH}_2\text{---}$, $-\text{COO---}$, $-\text{CONH---}$, $-\text{O---}$, $-\text{S---}$, and $-\text{OSO}_2\text{O---}$.
9. The polymer of claim 7 wherein R_{10} is $-(\text{CH}_2\text{CH}_2)\text{---}$ or $-\text{C}(\text{CH}_3)_2\text{CH}_2\text{CH}_2\text{---}$.
10. The polymer of claim 1 wherein "c" is 0.
11. The polymer of claim 1 wherein "d" is 0.
12. The polymer of claim 1 wherein the pendant group on Q_1 capable of forming hydrogen bonds is $-\text{CONH}_2$.
13. The polymer of claim 1 wherein the pendant group on Q_1 capable of forming covalent bonds is $-\text{CONHCHOHCHO}$.
14. The polymer of claim 1 wherein Q_1 has $-\text{CONH}_2$ and $-\text{CONHCHOHCHO}$ pendant groups.

15. A synthetic polymer having hydrogen bonding capability and containing one or more polysiloxane moieties, said polymer having the following structure:



where:

5 $w \geq 1$;

$\text{R}_1, \text{R}_1', \text{R}_2, \text{R}_3 = \text{H}$ or C_{1-4} alkyl;

$a, b > 0$;

$c, d \geq 0$ such that $c+d > 0$;

$\text{R}_0 =$ a group capable of forming hydrogen or covalent bonds with cellulose;

10 $\text{Q}_4 =$ a monomer unit or a block or graft copolymer containing a hydrophilic moiety;

$\text{A}_1 = -\text{H}, -\text{COOH}$;

$\text{R}_4 =$ a $\text{Z}_1 - \text{R}_6$ radical,

where:

$\text{Z}_1 =$ any radical capable of bonding the R_6 group to the polymer;

15 $\text{R}_6 =$ a block or graft copolymer containing siloxane bonds ;

$\text{R}_5 = \text{Z}_3 - \text{R}_{10} - \text{W}$,

where:

$\text{Z}_3 =$ any radical capable of bonding the R_{10} group to the polymer;

20 $\text{R}_{10} =$ any linear or branched, aliphatic or aromatic hydrocarbon of 2 or more carbons; and


$\text{W} = -\text{N}^+ \text{R}_{11}, \text{R}_{12}, \text{R}_{13}$, where $\text{R}_{11}, \text{R}_{12}, \text{R}_{13}$ are C_{1-4} alkyl groups.

16. The polymer of claim 15 wherein R_0 is selected from the group consisting of $-\text{CONH}_2$, $-\text{COOH}$, $-\text{COO}^-\text{M}^+$, $-\text{OH}$, $-\text{CONHCHOHCHO}$, and mixtures thereof, wherein M^+ is a counter ion.

17. The polymer of claim 15 wherein Q_4 is of the form $-\text{Z}_2 - \text{Q}_4 - \text{Z}_2'$ - where Z_2, Z_2' are bridging radicals, which can be the same or different.

18. The polymer of claim 15 wherein Z_1 is selected from the group consisting of aryl, $-\text{CH}_2-$, $-\text{COO}-$, $-\text{OOC}-$, $-\text{CONR}'-$, $-\text{NR}'\text{CO}-$, $-\text{O}-$, $-\text{S}-$, $-\text{OSO}_2\text{O}-$, $-\text{CONHCO}-$, $-\text{CONHCHOHCOHO}-$, $-\text{CONHCHOHCOHNH}-$, and where R' is H or C_{1-4} alkyl.

19. The polymer of claim 15 wherein Z_1 is selected from the group consisting of aryl, $-CH_2-$, $-COO-$, $-CONH-$, $-O-$, $-S-$, and $-OSO_2O-$.
20. The polymer of claim 15 wherein R_{10} is $-(CH_2CH_2)-$ or $-C(CH_3)_2CH_2CH_2-$.
21. The polymer of claim 15 wherein A_1 is $-H$ and R_0 is $-CONH_2$.
22. The polymer of claim 15 wherein A_1 is $-H$ and R_0 is $-CONHCHOHCHO$.
23. The polymer of claim 15 wherein R_0 consists of both $-CONH_2$ and $-CONHCHOHCHO$ groups.
24. A synthetic polymer having hydrogen bonding capability and containing one or more polysiloxane moieties, said polymer having the following structure:



where:

5 $w \geq 1$;

$R_1, R_1', R_2, R_3 = H$ or C_{1-4} alkyl;

$a, b > 0$;

$c, d \geq 0$ such that $c+d > 0$;

$R_0 =$ a group capable of forming hydrogen or covalent bonds with cellulose;

10 $Q_4 =$ a monomer unit or a block or graft copolymer containing a hydrophilic moiety;

$A_1 = -H, -COOH$;

$R_4 =$ a $Z_1 - R_6$ radical,


where:

$Z_1 =$ any radical capable of bonding the R_6 group to the polymer;

15 $R_6 =$ a block or graft copolymer containing siloxane bonds ;

25. A paper sheet comprising a synthetic polymer having hydrogen bonding capability and containing one or more polysiloxane moieties, said polymer having the following structure:

5



where:

10 $a, b > 0;$

$c, d \geq 0;$

$w \geq 1;$

$Q_1 =$ a monomer unit or a block or graft copolymer containing a pendant group capable of forming hydrogen or covalent bonds with cellulose;

15 $Q_2 =$ a block or graft copolymer containing siloxane bonds ;

$Q_3 =$ a monomer unit or a block or graft copolymer containing a charge functionality;
and

$Q_4 =$ a monomer unit or a block or graft copolymer containing a hydrophilic moiety,
which is desirable for making the material into a form suitable for papermaking.

20

26. The paper sheet of claim 25 wherein the pendant group on Q_1 capable of forming hydrogen or covalent bonds is selected from the group consisting of $-\text{CONH}_2$, $-\text{COOH}$, $-\text{COO}^-\text{M}^+$, $-\text{OH}$, $-\text{CONHCHOHCHO}$ and mixtures thereof, wherein M^+ is a counter ion.

27. The paper sheet of claim 25 wherein Q_2 is of the form $-\text{Z}_1-\text{Q}_2-\text{Z}_1'-$ where Z_1, Z_1' are bridging radicals, which can be the same or different.

28. The paper sheet of claim 25 wherein Q_4 is of the form $-\text{Z}_2-\text{Q}_4-\text{Z}_2'-$ where Z_2, Z_2' are bridging radicals, which can be the same or different.

29. The paper sheet of claim 25 wherein Q_4 is a radical of the form $-\text{CHR}_1\text{CR}_0\text{R}_1'-$ wherein R_0 is an aliphatic polyether derivative of the formula $-\text{[(CR}_2\text{R}_2')_x\text{O}]_y-\text{R}_3$
where:


R_1, R_1' is $-\text{H}$, C_{1-4} alkyl;

5 R_2, R_2' is $-\text{H}$ or $-\text{CH}_3$;

$x \geq 2;$


$y \geq 2;$ and

- 10 R_3 is a terminal group selected from the group consisting of $-\text{CH}_3$, $-\text{H}$, $-\text{C}_2\text{H}_5$, and $-\text{NH}_2$.



30. The paper sheet of claim 25 wherein Q_3 is
31. The paper sheet of claim 25 wherein Q_3 is a radical of the form $\text{---CHR}_1\text{CR}_0\text{R}_1'\text{---}$ wherein
- R_0 = a pendant group of the form $Z_1\text{---R}_{10}\text{---W}$ where Z_1 is a radical capable of bonding the R_{10} group to the polymer;
- 5 R_1 and R_1' are $-\text{H}$ or a C_{1-4} alkyl group;
- R_{10} = any linear or branched, aliphatic or aromatic hydrocarbon of 2 or more carbons; and
- $W = -\text{N}^+\text{R}_{11}\text{R}_{12}\text{R}_{13}$ where R_{11} , R_{12} , R_{13} is a C_{1-4} alkyl group.
32. The paper sheet of claim 31 wherein Z_1 is selected from the group consisting of aryl, $-\text{CH}_2\text{---}$, $-\text{COO---}$, $-\text{OOC---}$, $-\text{CONH---}$, $-\text{O---}$, $-\text{S---}$, $-\text{NHCO---}$ and $-\text{OSO}_2\text{O---}$.
33. The paper sheet of claim 31 wherein R_{10} is $-(\text{CH}_2\text{CH}_2)\text{---}$ or $-\text{C}(\text{CH}_3)_2\text{CH}_2\text{CH}_2\text{---}$.
34. The paper sheet of claim 25 wherein "c" is 0.
35. The paper sheet of claim 25 wherein "d" is 0.
36. The paper sheet of claim 25 wherein the pendant group on Q_1 capable of forming hydrogen bonds is $-\text{CONH}_2$.
37. The paper sheet of claim 25 wherein the pendant group on Q_1 capable of forming covalent bonds is $-\text{CONHCHOHCHO}$.
38. The paper sheet of claim 25 wherein Q_1 has $-\text{CONH}_2$ and $-\text{CONHCHOHCHO}$ pendant groups.

39. A paper sheet comprising a synthetic polymer having hydrogen bonding capability and containing one or more polysiloxane moieties, said polymer having the following structure:



5 where:

$w \geq 1$;

$\text{R}_1, \text{R}_1', \text{R}_2, \text{R}_3 = \text{H or C}_{1-4} \text{ alkyl}$;

$a, b > 0$;

$c, d \geq 0$;

10 $\text{R}_0 =$ a group capable of forming hydrogen or covalent bonds with cellulose;

$\text{Q}_4 =$ a monomer unit or a block or graft copolymer containing a hydrophilic moiety;

$\text{A}_1 =$ $-\text{H}, -\text{COOH}$;

$\text{R}_4 =$ a $\text{Z}_1 - \text{R}_6$ radical,

where:

15 $\text{Z}_1 =$ any radical capable of bonding the R_6 group to the polymer;

$\text{R}_6 =$ a block or graft copolymer containing siloxane bonds ;

$\text{R}_5 = \text{Z}_3 - \text{R}_{10} - \text{W}$,

where:

20 $\text{Z}_3 =$ any radical capable of bonding the R_{10} group to the polymer;

$\text{R}_{10} =$ any linear or branched, aliphatic or aromatic hydrocarbon of 2 or more carbons; and


$\text{W} = -\text{N}^+ \text{R}_{11}, \text{R}_{12}, \text{R}_{13}$, where $\text{R}_{11}, \text{R}_{12}, \text{R}_{13}$ are C_{1-4} alkyl groups.

40. The paper sheet of claim 39 wherein R_0 is selected from the group consisting of $-\text{CONH}_2$, $-\text{COOH}$, $-\text{COO}^-\text{M}^+$, $-\text{OH}$, $-\text{CONHCHOHCHO}$, and mixtures thereof, wherein M^+ is a counter ion.

41. The paper sheet of claim 39 wherein Q_4 is of the form $-\text{Z}_2 - \text{Q}_4 - \text{Z}_2'$ - where Z_2, Z_2' are bridging radicals, which can be the same or different.

42. The paper sheet of claim 39 wherein Z_1 is selected from the group consisting of aryl, $-\text{CH}_2-$, $-\text{COO}-$, $-\text{OOC}-$, $-\text{CONR}'-$, $-\text{NR}'\text{OC}-$, $-\text{O}-$, $-\text{S}-$, $-\text{OSO}_2\text{O}-$, $-\text{CONHCO}-$, and $-\text{CONHCHOHCHOHO}-$, $-\text{CONHCHOHCHOHNH}-$ and where R' is H or C_{1-4} alkyl.

43. The paper sheet of claim 39 wherein Z_1 is selected from the group consisting of aryl, $-\text{CH}_2-$, $-\text{COO}-$, $-\text{CONH}-$, $-\text{O}-$, $-\text{S}-$, and $-\text{OSO}_2\text{O}-$.
44. The paper sheet of claim 39 wherein R_{10} is $-(\text{CH}_2\text{CH}_2)-$ or $-\text{C}(\text{CH}_3)_2\text{CH}_2\text{CH}_2-$.
45. The paper sheet of claim 39 wherein A_1 is $-\text{H}$ and R_0 is $-\text{CONH}_2$.
46. The paper sheet of claim 39 wherein A_1 is $-\text{H}$ and R_0 is $-\text{CONHCHOHCHO}$.
47. The paper sheet of claim 39 wherein R_0 consists of both $-\text{CONH}_2$ and $-\text{CONHCHOHCHO}$ groups .
48. A paper sheet comprising a synthetic polymer having hydrogen bonding capability and containing one or more polysiloxane moieties, said polymer having the following structure:



5 where:

 $w \geq 1:$

$R_1, R_1', R_2, R_3 = H \text{ or } C_{1-4} \text{ alkyl;}$

 $a, b > 0;$ $c, d \geq 0$ such that $c + d > 0$;

10 $R_0 =$ a group capable of forming hydrogen or covalent bonds with cellulose;

Q_4 = a monomer unit or a block or graft copolymer containing a hydrophilic moiety;

$$A_1 = -H, -COOH;$$
$$R_4 = aZ_1 - R_6,$$

where:

15 $Z_1 =$ any radical capable of bonding the R_6 group to the polymer;

$R_6 =$ a block or graft copolymer containing siloxane bonds ;

49. A method of making a paper sheet comprising the steps of: (a) forming an aqueous suspension of papermaking fibers; (b) depositing the aqueous suspension of papermaking fibers onto a forming fabric to form a web; and (c) dewatering and drying the web to form a paper sheet, wherein a synthetic polymer is added to the aqueous suspension of fibers and/or the web, said polymer having the following structure:

where:

10 $a, b > 0;$

$c, d \geq 0;$


$w \geq 1;$

$Q_1 =$ a monomer unit or a block or graft copolymer containing a pendant group capable of forming hydrogen or covalent bonds with cellulose;

15 $Q_2 =$ a block or graft copolymer containing siloxane bonds ;

$Q_3 =$ a monomer unit or a block or graft copolymer containing a charge functionality; and

$Q_4 =$ a monomer unit or a block or graft copolymer containing a hydrophilic moiety, which is desirable for making the material into a form suitable for papermaking.



50. The method of claim 49 wherein the pendant group on Q_1 capable of forming hydrogen or covalent bonds is selected from the group consisting of $-\text{CONH}_2$, $-\text{COOH}$, $-\text{COO}^-\text{M}^+$, $-\text{OH}$, $-\text{CONHCHOHCHO}$ and mixtures thereof, wherein M^+ is a counter ion.

51. The method of claim 49 wherein Q_2 is of the form $-\text{Z}_1-\text{Q}_2-\text{Z}_1'$ where Z_1 , Z_1' are bridging radicals, which can be the same or different.

52. The method of claim 49 wherein Q_4 is of the form $-\text{Z}_2-\text{Q}_4-\text{Z}_2'$ where Z_2 , Z_2' are bridging radicals, which can be the same or different.

53. The method of claim 49 wherein Q_4 is a radical of the form $-\text{CHR}_1\text{CR}_0\text{R}_1'-$ wherein R_0 is an aliphatic polyether derivative of the formula $-\text{[(CR}_2\text{R}_2')_x\text{O}]_y-\text{R}_3$ where:

R_1 , R_1' is $-\text{H}$, C_{1-4} alkyl;


5 R_2 , R_2' is $-\text{H}$ or $-\text{CH}_3$;

$x \geq 2$;

$y \geq 2$; and

R_3 is a terminal group selected from the group consisting of $-\text{CH}_3$, $-\text{H}$, $-\text{C}_2\text{H}_5$, and $-\text{NH}_2$.

10



54. The method of claim 49 wherein Q_3 is

55. The method of claim 49 wherein Q_3 is a radical of the form $\text{---CHR}_1\text{CR}_0\text{R}_1'\text{---}$ wherein

R_0 = a pendant group of the form $Z_1\text{---R}_{10}\text{---W}$, where Z_1 is a radical capable of bonding the R_{10} group to the polymer;

5 R_1 and R_1' are $-\text{H}$ or a C_{1-4} alkyl group;

R_{10} = any linear or branched, aliphatic or aromatic hydrocarbon of 2 or more carbons; and

$W = \text{---N}^+\text{R}_{11}\text{R}_{12}\text{R}_{13}$ where R_{11} , R_{12} , R_{13} is a C_{1-4} alkyl group.

56. The method of claim 55 wherein Z_1 is selected from the group consisting of aryl, $-\text{CH}_2\text{---}$, $-\text{COO---}$, $-\text{CONH---}$, $-\text{O---}$, $-\text{S---}$, and $-\text{OSO}_2\text{O---}$.

57. The method of claim 55 wherein R_{10} is $-(\text{CH}_2\text{CH}_2)\text{---}$ or $-\text{C}(\text{CH}_3)_2\text{CH}_2\text{CH}_2\text{---}$.

58. The method of claim 49 wherein "c" is 0.


59. The method of claim 49 wherein "d" is 0.

60. The method of claim 49 wherein the pendant group on Q_1 capable of forming hydrogen bonds is $-\text{CONH}_2$.

61. The method of claim 49 wherein the pendant group on Q_1 capable of forming covalent bonds is $-\text{CONHCHOHCHO}$.

62. The method of claim 49 wherein Q_1 has $-\text{CONH}_2$ and $-\text{CONHCHOHCHO}$ pendant groups.

63. A method of making a paper sheet comprising the steps of: (a) forming an aqueous suspension of papermaking fibers; (b) depositing the aqueous suspension of papermaking fibers onto a forming fabric to form a web; and (c) dewatering and drying the web to form a paper sheet, wherein a synthetic polymer is added to the aqueous suspension of fibers and/or the web, said polymer having the following structure:



where:

$w \geq 1$;

$\text{R}_1, \text{R}_1', \text{R}_2, \text{R}_3 = \text{H or C}_{1-4} \text{ alkyl}$;

10 $a, b > 0$;

$c, d \geq 0$;

$\text{R}_0 =$ a group capable of forming hydrogen or covalent bonds with cellulose;

$\text{Q}_4 =$ a monomer unit or a block or graft copolymer containing a hydrophilic moiety;

$\text{A}_1 = -\text{H}, -\text{COOH}$;

15 $\text{R}_4 =$ a $\text{Z}_1 - \text{R}_6$ radical,

where:

$\text{Z}_1 =$ any radical capable of bonding the R_6 group to the polymer;

$\text{R}_6 =$ a block or graft copolymer containing siloxane bonds ;

20 $\text{R}_5 = \text{Z}_3 - \text{R}_{10} - \text{W}$,

where:

$\text{Z}_3 =$ any radical capable of bonding the R_{10} group to the polymer;

$\text{R}_{10} =$ any linear or branched, aliphatic or aromatic hydrocarbon of 2 or more carbons; and


25 $\text{W} = -\text{N}^+ \text{R}_{11}, \text{R}_{12}, \text{R}_{13}$, where $\text{R}_{11}, \text{R}_{12}, \text{R}_{13}$ are C_{1-4} alkyl groups.

64. The method of claim 63 wherein R_0 is selected from the group consisting of $-\text{CONH}_2$, $-\text{COOH}$, $-\text{COO}^-\text{M}^+$, $-\text{OH}$, $-\text{CONHCHOHCHO}$, and mixtures thereof, wherein M^+ is a counter ion.

65. The method of claim 63 wherein Q_4 is of the form $-\text{Z}_2 - \text{Q}_4 - \text{Z}_2'$ where Z_2, Z_2' are bridging radicals, which can be the same or different.

66. The method of claim 63 wherein Z_1 is selected from the group consisting of aryl, $-\text{CH}_2-$, $-\text{COO}-$, $-\text{OOC}-$, $-\text{CONR}'-$, $-\text{NR}'\text{CO}-$, $-\text{O}-$, $-\text{S}-$, $-\text{OSO}_2\text{O}-$, $-\text{CONHCO}-$, and $-\text{CONHCHOHCOHO}-$, $\text{CONHCHOHCOHNH}-$, and where R' is H or C_{1-4} alkyl.
67. The method of claim 63 wherein Z_1 is selected from the group consisting of aryl, $-\text{CH}_2-$, $-\text{COO}-$, $-\text{CONH}-$, $-\text{O}-$, $-\text{S}-$, and $-\text{OSO}_2\text{O}-$.
68. The method of claim 63 wherein R_{10} is $-(\text{CH}_2\text{CH}_2)-$ or $-\text{C}(\text{CH}_3)_2\text{CH}_2\text{CH}_2-$.
69. The method of claim 63 wherein A_1 is $-\text{H}$ and R_0 is $-\text{CONH}_2$.
70. The method of claim 63 wherein A_1 is $-\text{H}$ and R_0 is $-\text{CONHCHOHCHO}$.
71. The method of claim 63 wherein R_0 consists of both $-\text{CONH}_2$ and $-\text{CONHCHOHCHO}$ groups.

72. A method of making a paper sheet comprising the steps of: (a) forming an aqueous suspension of papermaking fibers; (b) depositing the aqueous suspension of papermaking fibers onto a forming fabric to form a web; and (c) dewatering and drying the web to form a paper sheet, wherein a synthetic polymer is added to the aqueous suspension of fibers and/or the web, said polymer having the following structure:



where:

 $w \geq 1;$

$R_1, R_1', R_2, R_3 = H \text{ or } C_{1-4} \text{ alkyl;}$

```
10    a, b > 0;
```

 $c, d \geq 0$ such that $c + d > 0$;

R_0 = a group capable of forming hydrogen or covalent bonds with cellulose;

Q_4 = a monomer unit or a block or graft copolymer containing a hydrophilic moiety;

$$A_1 = -H, -COOH;$$

15 $R_4 = a Z_1 - R_6,$

where:

Z_1 = any radical capable of bonding the R_6 group to the polymer;

R_6 = a block or graft copolymer containing siloxane bonds.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/01614

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08G77/442 D21H17/59

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F C08G D06M D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 852 095 A (KAMIYAMA YASUYUKI ET AL) 22 December 1998 (1998-12-22) column 1, line 24 - line 28 column 4, line 34 column 4, line 52 columns 5, 6, formulae 2-7 column 11, line 35 column 13, line 53 - line 57 column 22, line 49 --- -/-	1, 3, 4, 25, 27, 28, 48, 51, 52

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

15 May 2000

Date of mailing of the international search report

22/05/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Hoepfner, W

Copied from 09866025 on 02-01-2004

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 723 022 A (DAUPLAISE DAVID LOUIS ET AL) 3 March 1998 (1998-03-03) column 1, line 3 - line 16 column 7, line 20 - line 21 examples A-D -----	2, 5-24, 26, 29-48, 50, 53-72
A	US 5 507 914 A (SARKAR JAWED M ET AL) 16 April 1996 (1996-04-16) column 2, line 60 - line 61 claims 1, 5 -----	2, 5-24, 26, 29-48, 50, 53-72

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US 00/01614

Box I Observations where certain claims were found unsearchable (Continuation of Item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☒ Claims Nos.: 1-14, 25-38, 49-62
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
see FURTHER INFORMATION sheet PCT/ISA/210
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of Item 2 of first sheet)

This International Searching Authority found multiple inventions in this International application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/SA/ 210

Continuation of Box I.2

Claims Nos.: 1-14,25-38,49-62

Present claims 1-14,25-38,49-62 relate to an extremely large number of possible compounds. Support within the meaning of Article 6 PCT and/or disclosure within the meaning of Article 5 PCT is to be found, however, for only a very small proportion of the compounds claimed. In the present case, the claims so lack support, and the application so lacks disclosure, that a meaningful search over the whole of the claimed scope is impossible. Moreover, functional definitions such as "capable of forming hydrogen ... bonds" (claims 1,15,24,25,29,49,63,72) or "desirable for making ... suitable for papermaking" (claims 1, 25, 49) appear to relate to the result to be achieved rather than to (a) means to arrive at the desired result (desiderata claims).

Consequently, the search has been carried out for those parts of the application which appear to be supported and disclosed, namely to the proposed Synthesis Examples of the description (pages 11-27) and to the remaining claims .

The applicant's attention is drawn to the fact that claims, or parts of claims, relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure.

INTERNATIONAL SEARCH REPORT

Information on patent family members

In tional Application No

PCT/US 00/01614

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5852095 A	22-12-1998	CA 2180839 A	02-11-1995
		CN 1142834 A	12-02-1997
		EP 0757059 A	05-02-1997
		WO 9529196 A	02-11-1995
		JP 8003409 A	09-01-1996
		KR 174804 B	01-04-1999
		SG 45098 A	16-01-1998
US 5723022 A	03-03-1998	AU 711664 B	21-10-1999
		AU 3400197 A	09-02-1998
		BR 9710237 A	10-08-1999
		CA 2260194 A	22-01-1998
		EP 0910700 A	28-04-1999
		NO 990079 A	11-01-1999
		WO 9802611 A	22-01-1998
US 5507914 A	16-04-1996	US 5501770 A	26-03-1996
		BR 9503623 A	16-04-1996
		CA 2155906 A	13-02-1996
		DE 69507858 D	25-03-1999
		DE 69507858 T	26-08-1999
		EP 0696663 A	14-02-1996
		FI 953826 A	13-02-1996
		JP 8092889 A	09-04-1996

Copied from 09866025 on 02-01-2004